



**Product Data Sheet &
General Processing Conditions**

**ZOVGOV® M25G4FR UV
Polybutylene Terephthalate (PBT)
Glass Fiber
Flame Retardant
UL94 V-0
UV stabilized**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.56	1.56	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0040 - 0.0060 in/in	0.40 - 0.60 %	D 955
Water Absorption, 24 hrs @ 23°C	0.070 %	0.070 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	10.0 ft-lbs/in	534 J/m	D 4812
Tensile Strength	16000 psi	110 MPa	D 638
Tensile Elongation	3.0 - 4.0 %	3.0 - 4.0 %	D 638
Tensile Modulus	1.20 x 10 ⁶ psi	8274 MPa	D 638
Flexural Strength	24000 psi	165 MPa	D 790
Flexural Modulus	1.00 x 10 ⁶ psi	6895 MPa	D 790
Hardness Rockwell, R	118	118	D 785

ELECTRICAL

Dielectric Strength, S/T, in oil	500 VPM	19.7 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	3.5	3.5	D 150
Dissipation Factor, 1 MHz, Dry	0.0200	0.0200	D 150
Volume Resistivity	> 1E16 ohm.cm	> 1E16 ohm.cm	D 257

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	375 °F	191 °C	D 648
@ 66 psi (455 kPa)	410 °F	210 °C	D 648
Ignition Resistance* Flammability	V-0 @ 1/32 in	V-0 @ 0.8 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	460 - 520 °F	238 - 271 °C
Mold Temperature	175 - 225 °F	79 - 107 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.03 %	0.03 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES