



# PEEK ZOVGOV<sup>®</sup> M330CA30

Test Item	Test Method	Conditions	Units	Test Data
<b>Mechanical Data</b>				
Tensile Strength	ISO 527	Break, 23°C	MPa	250
Tensile Elongation	ISO 527	Break, 23°C	%	1.5
Flexural Strength	ISO 178	Break, 23°C	MPa	360
Flexural Modulus	ISO 178	23°C	GPa	21
Compressive Strength	ISO 604	23°C	MPa	300
Charpy Impact Strength	ISO 179/1eA	Notched	$\text{kJ m}^{-2}$	6
	ISO 179/1U	Unnotched	$\text{kJ m}^{-2}$	40
Izod Impact Strength	ISO 180/A	Notched	$\text{kJ m}^{-2}$	8
	ISO 180/U	Unnotched	$\text{kJ m}^{-2}$	40
Mould Shrinkage	ISO 294-4	Along Flow	%	0.1
		Across Flow	%	0.5
<b>Thermal Data</b>				
Melting Point	ISO 11357	-	°C	343
Glass Transition (T <sub>g</sub> )	ISO 11357	Onset	°C	143
Special Heat Capacity	DSC	23°C	$\text{kJ kg}^{-1} \text{°C}^{-1}$	1.8
Coefficient of Thermal Expansion	ISO 11359	Along flow below T <sub>g</sub>	$\text{ppm K}^{-1}$	5
		Along flow above T <sub>g</sub>	$\text{ppm K}^{-1}$	6
Heat Deflection Temperature	ISO 75	1.8 Mpa	°C	339
Thermal Conductivity	ISO 22007-4	23°C	$\text{W m}^{-1} \text{K}^{-1}$	0.95
<b>Flow</b>				
Melt Index	ISO 1133	380°C,5kg	$\text{g 10min}^{-1}$	27
<b>Miscellaneous</b>				
Density	ISO 1183	Crystalline	$\text{g cm}^{-3}$	1.4
		Amorphous	$\text{g cm}^{-3}$	-
Shore D Hardness	ISO 868	23°C		88
Water Absorption (3.2mm thick Tensile Bar) (by immersion)	ISO 62	24h, 23°C	%	0.04
		Equilibrium, 23°C	%	0.3



## Electrical Data

Dielectric Strength	IEC 60243-1	2mm	kV mm <sup>-1</sup>	-
Comparative Tracking Index	IEC 60112	-	V	-
Dielectric Constant	IEC 60250	23°C, 1kHz	-	-
		23°C, 50Hz	-	-
Loss Tangent	IEC 60250	23°C, 1MHz	-	-
Volume Resistivity	IEC 60093	23°C, 1V	Ω cm	10 <sup>5</sup>
		275°C	Ω cm	-

\*Result based on similar products