



**Product Data Sheet &
General Processing Conditions**

**ZOVGOV® M23
Acetal (POM)
Base Resin**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	0 %	0 %	
Specific Gravity	1.41	1.41	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0170 - 0.0290 in/in	1.70 - 2.90 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	28.0 ft-lbs/in	1495 J/m	D 4812
Tensile Strength	8700 psi	60 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.35 x 10 ⁶ psi	2413 MPa	D 638
Flexural Strength	11000 psi	76 MPa	D 790
Flexural Modulus	0.35 x 10 ⁶ psi	2413 MPa	D 790

ELECTRICAL

Dielectric Strength, S/T, in air	500 VPM	19.7 kV/mm	D 149
----------------------------------	---------	------------	-------

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per MOLAN Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	360 - 425 °F	182 - 218 °C
Mold Temperature	175 - 225 °F	79 - 107 °C
Drying	2 hrs @ 250 °F	2 hrs @ 121 °C
Moisture Content	0.15 %	0.15 %
Dew Point	-25 °F	-32 °C

PROCESSING NOTES

Desiccant Type Dryer Required.